

## PRODUCT INFORMATION PAGE

# URETHANE 100

---

### TWO-PART POLYURETHANE ADHESIVE

---

**PROPERTIES:**

A two-part polyurethane adhesive for general use. It does not contain solvents and water. The product has extra high filling properties. After binding, it presents very good stability and no shrinkage with even thicker layers. It is characterized by a long open time, which lasts up to 100 minutes. The adhesive complies with DIN 281 and PN EN 14293 norms.

**PURPOSE:**

For bonding on a following surfaces: concrete, anhydrite, ceramic (after appropriate preparation) and wooden – solid, layered and exotic parquet, as well as solid and layered boards, wooden panels or readymade and industrial parquet (including the underfloor heating)

**SURFACE PREPARATION:**

The surface and climatic conditions in the room must be consistent with general parquetry principles. The substrate must be even, dry, stable and cleaned of any residues of oil, paint, plaster, etc., which prevent good adhesion. It also needs to be resistant to shearing and peeling, which result from "work" of any wood material. We recommend priming the substrate with polyurethane primer, such as RENOPRIMER PU 112, 150, 200 or 300.

**INSTRUCTIONS:**

Add component B to component A (mass) and combine them thoroughly. Use a suitable mixing tool. Mix until the whole product is smooth. If not carefully mixed, the product will not achieve full effectiveness. Apply the adhesive to the substrate with a notched trowel. Press lightly and move horizontally on the glued elements. Do not walk on the glued surfaces for 4 – 6 hours.

**IMPORTANT NOTICE:**

Dividing the product into portions entails a strong risk that the adhesive may lose its effectiveness due to incorrect proportions. However, if there is a necessity for portioning the product, the B component must be dosed carefully with A component. It is not allowed to glue elements of the flooring, if the temperature is under +15°C and ambient humidity is above 65%. Use PU Cleaner to clean tools and to remove dirt resulting from parquet work. After hardening, glue can be removed mechanically only.

**EFFICIENCY:**

For information purposes, we provide size of notched trowels used for gluing. It is important to choose the correct size of a notched trowel to ensure complete and efficient coverage of the underside of the floor elements. If necessary, enlarge teeth of the trowel with sheet metal shears.

|  |                   |  |
|--|-------------------|--|
| Floor type:<br>Wooden floors             | Toothing:<br>B 13 | Efficiency:<br>1100-1300g/m <sup>2</sup> |
| Layered boards,<br>wooden panels         | B 11              | 1000-1200g/m <sup>2</sup>                |
| Readymade parquet,<br>industrial parquet | B 11              | 1000-1200g/m <sup>2</sup>                |

**STORAGE:**

The product should be stored in the unopened, original packaging in a dry area at a temperature of +5°C to +25°C

**SPECIFICATIONS:**

A component – mass

B component - hardener

Form: Thick liquid (A cpnt)

Oily liquid (B cpnt)

Colour: Gray (A cpnt)

Brown (B cpnt)

Smell: Odourless (A cpnt)

Earthy (B cpnt)

Boiling point: 190°C

Ignition point: 250°C (A cpnt)

200°C (B cpnt)

Density: 1.6kg/dm<sup>3</sup> (A cpnt)

1.2kg/dm<sup>3</sup> (B cpnt)

Expiration: 12 months from the production date on the packaging

Package: 9.99kg (A cpnt + B cpnt)

PN: 0950

---

For difficult problem-solving questions, or products with special requirements, which are not covered by this technical card, we assure all our clients of our professional consulting services. Upon issue of a new technical card, the present one will no longer be valid.